Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-03-16-13**

Date: 20/03/2018

Customer : Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.

Address : Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to CC roads and drains at difence colony in Bagalagunte ward No.14.

Agency : Sri. BT Hanumantharaju, H No.1334, Anjanadri.7th Main , 11th Cross, WOC Road, 2nd Stage Mahalakshmipuram, Bangalore-560088

Customer's Reference : EE/DD/WO/256/17-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 16-03-18

Sample ID No : 2018-03-16-13 /05

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M40 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 20/03/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M40	13/03/2018	20/03/2018	151.28 X 151.98 X 151.37	22992	8.196	777.1	33.8	33.7
2	Cement Concrete Pavement	M40	13/03/2018	20/03/2018	151.22 X 151.72 X 149.63	22943	8.208	768.6	33.5	
3	Cement Concrete Pavement	M40	13/03/2018	20/03/2018	150.49 X 150.77 X 151.08	22689	8.219	764.6	33.7	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-03-16-13** **Date: 10/04/2018**

Customer : Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.

Address : Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to CC roads and drains at difence colony in Bagalagunte ward No.14.

Agency : Sri. BT Hanumantharaju, H No.1334, Anjanadri.7th Main , 11th Cross, WOC Road, 2nd Stage Mahalakshmipuram, Bangalore-560088

Customer's Reference : EE/DD/WO/256/17-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 16-03-18

Sample ID No : 2018-03-16-13 /06

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 ~~mm~~

Sample grade/Age : M40 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M40	13/03/2018	10/04/2018	149.63 X 151.28 X 150.44	22636	8.176	991.5	43.8	43.5
2	Cement Concrete Pavement	M40	13/03/2018	10/04/2018	150.38 X 149.28 X 151.33	22449	8.204	967.5	43.1	
3	Cement Concrete Pavement	M40	13/03/2018	10/04/2018	150.75 X 151.72 X 150.38	22872	8.168	994.9	43.5	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP-2018-03-16-13** **Date: 19/03/2018**
Customer	:	Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to CC roads and drains at difence colony in Bagalagunte ward No.14.
Agency	:	Sri. BT Hanumantharaju, H No.1334, Anjanadri.7th Main , 11th Cross, WOC Road, 2nd Stage Mahalakshmipuram, Bangalore-560088
Customer's Reference	:	EE/DD/WO/256/17-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	16-03-18
Sample ID No	:	2018-03-16-13 /03
Customer ID	:	Cement Concrete Pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M40 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	19/03/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M40	12/03/2018	19/03/2018	150.44 X 150.39 X 151.28	22625	8.284	764.7	33.8	33.7
2	Cement Concrete Pavement	M40	12/03/2018	19/03/2018	151.75 X 150.75 X 151.87	22876	8.156	766.4	33.5	
3	Cement Concrete Pavement	M40	12/03/2018	19/03/2018	151.98 X 151.39 X 150.75	23008	8.196	775.4	33.7	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2018-03-16-13** **Date: 09/04/2018**

Customer : Assistant Executive Engineer, Dasarahalli Sub Division, BBMP, Bangalore.

Address : Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Improvements to CC roads and drains at difence colony in Bagalagunte ward No.14.

Agency : Sri. BT Hanumantharaju, H No.1334, Anjanadri.7th Main , 11th Cross, WOC Road, 2nd Stage Mahalakshmipuram, Bangalore-560088

Customer's Reference : EE/DD/WO/256/17-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 16-03-18

Sample ID No : 2018-03-16-13 /04

Customer ID : Cement Concrete Pavement

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M40 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 09/04/2018

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete Pavement	M40	12/03/2018	09/04/2018	151.98 X 150.47 X 150.39	22868	8.153	967.3	42.3	42.5
2	Cement Concrete Pavement	M40	12/03/2018	09/04/2018	151.22 X 150.46 X 150.53	22753	8.198	957.9	42.1	
3	Cement Concrete Pavement	M40	12/03/2018	09/04/2018	150.79 X 150.88 X 150.76	22751	8.142	982.9	43.2	

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig Date BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com